

## POLYSPORT 1052-GLOSSY

UV-RESISTANT, POLYURETHANE-BASED, TWO-COMPONENT, GLOSSY, FINISH ALIPHATIC COATING

### GENERAL CHARACTERISTICS

**POLYSPORT 1052-GLOSSY** is a polyurethane, two-component, solvent-based, with glossy finish aliphatic coating for outdoor sports surfaces.

- It is applied as a final, sealing layer on top of playground floorings made of **SBR rubber granules** plus **PU binder** mixture, or **EPDM** plus **PU binder** mixture, on safety tiles and on top of polyurethane outdoor sports systems such as **POLYFLEX PU-EX**.
- It is UV-resistant and thus absolutely suitable for outdoor surfaces, including running tracks, for UV-protection in case of sensitive, light colors such as blue, orange, green.
- Ideal for protection of EPDM rubber flooring.

### TECHNICAL DATA

Basis:	two-component polyurethane paint
Appearance:	liquid
Colors:	KDF colorchart
Viscosity(250C):	200 - 600 mPas
Density(250C):	1.08 - 1.18 kg/l <sup>7</sup>
Mixing proportion (A:B):	78 : 22 by weight
Temperature for the application and drying of the material	15 – 40oC

### PREPARATION-APPLICATION

**Applied on dry surfaces without rising humidity issues, free of materials that might prevent bonding e.g. dust, loose particles, grease etc (in case of asphalt or concrete).** The success in the application depends on the right preparation of the underlay and use of the material.

- Good, dry cleaning of the surface from dust and residues using vacuum cleaner and squeegee.
- Caution must be taken so that temperature of the support surface as well as ambient air remains above 15° C during application and curing of the materials while relative humidity does not exceed 75%.
- The A component should be thoroughly stirred to incorporate any slight separation, while continuing stirring, the hardener (B component) should be added. Continue stirring until a homogeneous mix is obtained.
- The application is done by airless sprayer or short-haired mohair roller in 2 crossing layers.

## CONSUMPTION

200-250 gr/m<sup>2</sup> on polyurethane floorings

400-500 gr/m<sup>2</sup> on running tracks or EPDM surfaces.

Apply two layers at least.

## APPLICATION TOOLS

Short-haired mohair roller or airless sprayer. Tools should be cleaned with **PU SOLVENT** immediately after use.



## PACKAGING

Supplied in set of 20 Kg (two drums).



## STORAGE

12 months in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30°C (avoid sunlight).

## REMARKS

- Working time of **POLYSPORT 1052-GLOSSY** decreases when ambient temperature rises.
- Prolonged storage of partially used containers, containing **POLYSPORT 1052-GLOSSY** must be avoided, as contact with atmospheric moisture could possibly cause clouding of the product.
- After hardening **POLYSPORT 1052-GLOSSY** is completely safe for health.
- The second layer of **POLYSPORT 1052-GLOSSY** has to be applied strictly within 24 hours, depending on the temperature and humidity (European conditions) **or within 3-6 hours (GCC high-temperature conditions)** in order to cover the surface swiftly and protect it from unwanted weather or other adverse conditions (sand dust, accumulated dirt or foreign matter etc.). In case the 24-hour limit (Europe) or the 3-6-hour limit (GCC) is surpassed or weather or other adverse conditions interfere between layers at any time, the surface might need sanding again to restore smoothness and cleanliness before applying subsequent layers of the aliphatic top coat.

**CAUTION**

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

**For more information consult the safety data sheet.**

---

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.